



DIA-STRON
DELIVERING MEASUREMENT SOLUTIONS

Interfacial Shear Strength (IFSS) Module



Overview


The Interfacial Shear Strength module (IFSS) is an interchangeable module for the Dia-Stron LEX820, used to measure the debonding force of micro-droplets on single fibres and filaments. The camera and light source enable users to visualise the fibre/droplet during the test and capture the mode of failure in video and still images. The IFSS method can be applied to various fibre and filament types: glass, carbon, ceramic, aramid, basalt or natural fibres.

Principal features and benefits:

- Detailed interfacial shear data
- Image calibration and droplet measurements
- High speed video and image capture via USB connection
- High positional repeatability and accurate speed control
- Adjustable magnification (10 - 220x) and built-in polarisation

Applications:

- Interfacial shear strength properties
- Visualise and record mode of failure at the fibre/matrix interface



Metrology principle

The IFSS measurement is based on the universally recognised micro-bond method, which evaluates the interfacial properties of matrix resins on fibres and filaments commonly used in composite materials.

The IFSS module uses interchangeable precision laser cut tungsten slotted plates to support the micro-droplet whilst the specimen is withdrawn through. The sample is secured at the other end using the Dia-Stron one-part plastic tab system and held in place using pneumatic sample covers. The force being applied by the micro-droplet* to the plate is recorded by the load cell until interfacial failure.

The camera and light source enable capture of high speed images of the fibre and droplet, with the built-in polarisation filter suppressing glare from reflective materials such as metals, plastics and glass. The illumination system provides front and back lighting. The droplet location and size can be measured on captured images, and dynamic shearing behaviour can be recorded to identify the type of failure mode.

*Samples are mounted using the Dia-Stron one-part plastic tab system. Please note: it is the responsibility of the user to apply micro-droplets using thermoplastics or thermosets on the fibre when using the IFSS module.




Dedicated software – UvWin


The LEX820 system is controlled using Dia-Stron UvWin software. Method parameters can be easily edited within the software, and UvWin enables automatic data correction for system compliance.

UvWin also offers a number of integrated data processing tools and the raw data can be exported as a text file, for use in Excel or other statistical packages. UvWin is compatible with the latest versions of the Windows OS.

Sample image and data



Sisal fibre with an epoxy resin droplet



Debonding data for a polypropylene droplet from a Lyocell fibre

LEX820 Linear Extensometer

| | |
|-------------------------|------------------------------|
| Extension range | 3—53mm |
| Speed range | 0.01 to 2.6mm/sec |
| Force range | 0 to 2.5N or 0 to 20N |
| Force resolution | 0.05mN (2.5N) or 0.5mN (20N) |
| Displacement resolution | 1µm |
| Displacement accuracy | 50µm |
| Load cell linearity | ±0.1% full scale |

Shearing plates

| | |
|------------------------------------|--------------------------|
| Standard shearing plate slot sizes | 50µm, 80µm, 100µm, 200µm |
|------------------------------------|--------------------------|

Content

LEX820 Instrument
IFSS Module, including camera and illumination system
UV1000 Control Unit
PU1100 Pneumatic Unit
UvWin software for Windows OS

Requirements

| | |
|----------------|---|
| Power Supply | 85-265V AC 47-63Hz, 100W |
| Compressed Air | Dry and clean 4.5 Bar 20 l/min |
| Computer | Windows OS: 7 and 10 2 x USB 2.0 ports 1 x USB 3.0 port |

Imaging

| | |
|--------------|---|
| Illumination | White light, front (polarised) and back |
| Camera | 5 megapixel CMOS sensor 10 — 220x magnification Maximum frame rate 45fps Built-in polarisation |

Contact Us

Dia-Stron Ltd.

9 Focus Way
Andover, Hampshire
SP10 5NY | United Kingdom
T. +44(0) 1264 334700

Dia-Stron Inc.

9 Trenton Lakewood Road
Clarksburg, NJ
08510 | U.S.A.
T. +1 (609) 454 6008

Email: enquiry@diastron.com

www.diastron.com